

Archroma is a global color and specialty chemicals company committed to innovation, world-class quality standards, high service levels, cost-efficiency and sustainability. Headquartered in Pratteln, Switzerland, the company operates a highly integrated, customer-focused platform that delivers specialized performance and color solutions in over 90 countries.

/ CREATING SUSTAINABLE SOLUTIONS

Archroma's purpose is to lead our industry towards a more sustainable future for our customers and markets. We touch and color people's lives every day, everywhere. That is why, at Archroma, we continuously challenge the status quo in the deep belief that we can make our industry sustainable. We look at how we operate in a holistic way, in order to protect the health and safety of our people, our communities, our customers, the consumers, as well as the environment in order to preserve our Earth for us all and future generations.

/ CERTIFICATION

Archroma and all subsidiaries operate to global ISO standardized management systems:

SN EN ISO 9001:2015 Quality Management Systems Standard
SN EN ISO 14001:2015 Environmental Management Systems Standard
SN EN ISO 45001:2018 Occupational Health and Safety Management System Standard

Initial third-party audit and certification in 2014, re-certified in 2023 with a current validity until July 2026.



www.archroma.com
textileeffects@archroma.com

ARCHROMA MANAGEMENT LLC
Hardstrasse 1
4133 Pratteln
Switzerland

ARCHROMA TEXTILE EFFECTS
Archroma Singapore, Pte. Ltd.
1 International Business Park
#06-01 The Synergy
609917 Singapore

This information corresponds to the present state of our knowledge and is intended as a general description of our products and their possible applications. Archroma makes no warranties, express or implied, as to the information's accuracy, adequacy, sufficiency or freedom from defect and assumes no liability in connection with any use of this information. Any user of this product is responsible for determining the suitability of Archroma's products for its particular application. *Nothing included in this information waives any of Archroma's General Terms and Conditions of Sale, which control unless it agrees otherwise in writing. Any existing intellectual / industrial property rights must be observed. Due to possible changes in our products and applicable national and international regulations and laws, the status of our products could change. Material Safety Data Sheets providing safety precautions, that should be observed when handling or storing Archroma products, are available upon request and are provided in compliance with applicable law. You should obtain and review the applicable Material Safety Data Sheet information before handling any of these products. For additional information, please contact Archroma.

*For sales to customers located within the United States and Canada the following applies in addition :
NO EXPRESS OR IMPLIED WARRANTY IS MADE OF THE MERCHANTABILITY, SUITABILITY, FITNESS FOR A PARTICULAR PURPOSE OR OTHERWISE OF ANY PRODUCT OR SERVICE.

® Trademark of Archroma registered in many countries
© 2023 Archroma



Scan the QR code to learn more about our products

CERTIFIED TO
SE EN ISO 9001:2015
SN EN ISO 14001:2015
SN EN ISO 45001:2018



LUMAPLAST®

SOLVENT DYES
Colorants for industrial materials

VALUE PROPOSITION

LUMAPLAST® has the following characteristic as colorants for synthetic resins.

TRANSPARENCY & COLOR STRENGTH



LUMAPLAST® dyes contain a very low amount of impurities, allowing users to achieve vibrant and intense hues. This range of dyes offer excellent transparency and clarity, making them ideal for applications that require vibrant and clear colors.

HEAT & MIGRATION RESISTANCE



LUMAPLAST® dyes exhibit good heat stability with some colorants remaining stable at over 300°C (572°F) especially when used in engineering plastics. These dyes also display excellent resistance to migration when tested for 72hrs at 60°C under 5.1Kgs of pressure.

FASTNESS TO LIGHT AND WEATHER



LUMAPLAST® dyes ensure long-lasting results even in challenging environments where the color of the final product does not change even after long term exposure to light and weather.

COMPATIBILITY



LUMAPLAST® dyes are compatible with various resins:

- / Polystyrene.....(PS)
- / Polyamide(PA)
- / Styrene-acrylonitrile resin(AS)
- / Polyester(PE)
- / Acrylonitrile-butadiene-styren. (ABS)
- / Poly (methyl methacrylate)(PMMA)
- / Polycarbonate(PC)
- / Rigid polyvinyl chloride(Rigid PVC)
- / Polyphenylene resin(PP)
- / Poly Ethylene Terephthalate ... (PET)
- / Poly Butylene Terephthalate ... (PBT)

APPLICATIONS

PLASTICS AND ENGINEERING PLASTICS



LUMAPLAST® dyes are used in the production of various plastic articles such as packaging materials, containers, toys, and automotive parts. The dyes provide a transparent color of various polymers including PS, AS, ABS, PMMA, PET and PC.

SYNTHETIC FIBERS




LUMAPLAST® dyes are also suitable for coloration of synthetic fibers. It can be applied in spin-dyeing of polyester or polyamide fiber and is completely soluble in polymer to produce intense colors with excellent color fastness.

PAINT, COATING AND INKS



LUMAPLAST® dyes can be used in the formulation of paints for automotive coatings, industrial coatings and decorative paints to achieve a durable weather-resistant coloration. These dyes are commonly used in the formulation of ink for inkjet printers. These inks enable printers to achieve vibrant, long-lasting colors and can be used on various substrates.

OTHER USES



LUMAPLAST® dyes can be employed in the formulation of wood stains and varnishes for furniture, flooring, and other wood products, providing rich and transparent coloration while enhancing the natural beauty of the wood. It can also be used in various other applications like leather, waxes, meta foil, oils, and petroleum.

LUMAPLAST®		YELLOW 4G	YELLOW 3G	YELLOW GG	YELLOW HM	ORANGE HRP	ORANGE GG	RED HFG	RED H3G	RED A2G	RED GGL	RED BB	RED 5B	RED VIOLET RV	VIOLET R	VIOLET B	BLUE 2B	BLUE RR	BLUE R	GREEN G	GREEN 5BL	BLACK K	BLACK KB	Nigrosin Base BA		
	PMMA (Dye 0.02%)																									
	ABS (Dye 0.1%)																									
Colour Index Generic Name		SY 98	SY 93	SY 114	SY 163	SO 60	SO 63	SR 149	SR 135	SR 179	SR 111	SR 195	SR 52	SV 59	SV 31	SV 13	SB 104	SB 97	SB122	SG 28	SG 3	SK 3	SK 27	SK 7		
Physicals	Bulk density (mL/g)	9.8	7.6	9.5	5.4	38.4	6.7	3.7	14.5	3.3	19.9	3.6	7	21.2	2.2	8.4	14.9	17		13.5	9.9	17.2	18.7	-		
	Melting point(°C)	107	185	264	177	228	169	267	307	255	163	204	270	186	285	185	244	200	251	245	205	-	235	275		
	Sublimation (°C)	341	351	276	315	264	219	310	328	323	210	300	320	295	241	281	340	-	280	354	330	-	310	-		
Solubility	Toluene	2	0.1	0.09	4.92	0.33	1	0.23	0.05	0.37	0.89	-	0.07	3.1	0.04	0.45	0.2	-	-	-	0.79	-	0.2	4.6		
	Ethanol	0.01	0.96	0	0	0.01	0.1	<0.01	<0.001	0.01	0.05	0.08	0.01	0.15	0.01	0.02	0.04	0.03	-	<0.01	0.01	-	0.6	7		
	Acetone	0.05	2.35	0.04	1.33	0.09	0.5	0.03	0	0.07	0.52	0.14	0.02	4.2	0.03	0.26	0.19	0.3	-	0.2	0.09	-	-	-		
	Ethylacetate	0.09	1.4	0.04	1.2	0.12	0.5	0	0	0.1	0.54	-	0.02	-	0.04	0.25	-	1.1	-	0.45	0.18	-	0.3	2		
	DOP	0.2	0.47	0.08	0	0.07	-	-	0.01	0.17	0.29	-	0.07	-	0.03	0.18	-	-	-	-	0.13	-	-	-	-	
	THF	1.3	6.75	0.24	3.5	0.6	-	-	0.02	0.17	2.3	-	0.15	-	0.3	1.6	0.3	-	-	-	1.8	-	-	-	-	
	MMA	0.44	1.13	0.09	-	0.21	-	-	0.01	0.88	0.82	-	0.06	-	0.05	0.5	-	2	-	1	0.4	-	-	-	-	
Fastness	MEK	-	3.55	0.09	2.5	0.19	0.7	-	0.01	0.22	-	-	0.06	1.9	0.08	0.82	0.29	-	-	-	0.41	-	5	-		
	Bleeding	5	5	4-5	5	5	4-5	4-5	5	5	4-5	4-5	5	5	5	5	-	5	5	5	5	4-5	4-5	-		
	Heat	5	3	4-5	5	4-5	4-5	4-5	4-5	4-5	4-5	5	4-5	4-5	4-5	4-5	-	4-5	4-5	4-5	5	4	5	4		
Limitation	Light	4-5	6-7	6-7	7-8	6-7	6-7	5-6	7-8	8	6-7	7-8	5-6	7-8	5	6-7	7-8	5-6	7-8	7-8	7-8	7-8	7-8	4-5		
	R-PVC	R	HR	R	HR	HR	HR	R	HR	HR	R	R	HR	HR	R	HR	R	R	HR	R	HR	X	R	-		
	PS	HR	HR	HR	HR	HR	HR	HR	HR	HR	HR	HR	HR	HR	HR	HR	HR	HR	HR	HR	HR	HR	HR	HR	HR	
	ABS	HR	X	HR	HR	HR	HR	HR	HR	HR	HR	HR	HR	HR	HR	HR	HR	HR	HR	HR	HR	HR	HR	HR	HR	
	PMMA	R	R	HR	HR	HR	HR	HR	HR	HR	HR	HR	HR	HR	X	HR	HR	HR	HR	HR	HR	HR	HR	R		
	PC	HR	HR	HR	HR	HR	R	HR	HR	HR	HR	HR	HR	HR	HR	HR	HR	HR	HR	HR	HR	HR	X	HR	-	
	PET	HR	X	R	HR	HR	R	R	HR	HR	R	HR	HR	R	X	HR	HR	HR	HR	HR	HR	HR	X	HR	HR	
	PA (Nylon 6)	HR	X	X	R	R	R	HR	HR	HR	R	R	HR	HR	X	R	HR	HR	X	R	HR	X	R	-		
PA (Nylon 6/6)	HR	X	R	R	R	R	X	HR	HR	X	X	X	X	X	R	R	X	X	R	HR	X	R	-			

HR -Highly Recommended

R - Restricted Application

X - Not Recommended